

## Replacement Sheet

### In the specification:

Page 4, second paragraph:

Various plastics of different molecular weight can be used. Polyvinyl chloride (PVC) and polyolefin are preferred. Well suited is porous, filled polyolefin, which consists of a homogeneous mixture of 8 to 100 vol. % polyolefin with a molecular weight (weight average) of at least 300,000, a standard-load melt index of substantially 0, measured according to ASTM-D-1278-57T (condition E), and a reduced viscosity of not less than 4.0, measured with a solution of 0.02 g of the polyolefin in 100 g of decalin at 130°C, 0 to 92 vol. % filler and 0 to 40 vol. % plasticizer.

### In the claims:

17. (Amended) The aromatic and/or enticing baits of claim 14, wherein said bait is in the form selected from the group consisting of fish-catching devices, feed baskets, buoyancy blocks for fish-catching nets, basic lead sheathings, blinker casings, spinner casings, twistlers and parts thereof.